

Avery[®] UC 900-862-W Frosted Sparkle

Cast Vinyl Window Film

(Formerly Avery[®] Frosted Sparkle)

Features

- Brilliant visual sandblasted effect
- Excellent conversion properties on computerised cutters
- Easy cutting and weeding
- Outstanding durability and outdoor life
- Excellent dimensional stability
- Excellent UV, temperature, humidity and salt-spray resistance
- Excellent adhesion

Conversion

- | | |
|--|--|
| <input checked="" type="checkbox"/> Flat bed cutters | <input type="checkbox"/> Cold overlaminating |
| <input checked="" type="checkbox"/> Friction fed cutters | <input type="checkbox"/> Estat printing |
| <input checked="" type="checkbox"/> Die cutting | <input type="checkbox"/> Water based inkjet |
| <input type="checkbox"/> UV Cured inkjet | <input type="checkbox"/> Solvent inkjet |
| | <input type="checkbox"/> Mild solvent inkjet |

Uses

Avery UC 900-862-W Frosted Sparkle films are designed to create the image of sand blasted decorations on glass without the use of physical sand blasting techniques and is also suitable for functional and manifestation graphics. Avery Frosted Sparkle can be applied to flat surfaces and produces best results when applied to transparent substrates such as glass, acrylic sheeting, and polycarbonate.

Description



Film: 60 micron cast vinyl film with sand blasted effect



Adhesive: Permanent acrylic in Australia/NZ



Backing: One side coated bleached Kraft paper, 140gsm



Outdoor life: Asia Pacific
Up to 5 years on the outside of external windows

Indoor life: Asia Pacific
Up to 7 years on the inside of external windows
Up to 15 years without direct UV light exposure

Common Applications

- Window graphics
- Architectural signage

Physical characteristics

General

Caliper, facefilm	ISO 534	60 micron
Caliper, facefilm & adhesive	ISO 534	90 micron
Dimensional stability	DIN 30646	0.2 mm max
Tensile strength	DIN 53455	22 N/mm ²
Elongation	DIN 53455	25%
Gloss	ISO 2813, 20°	15 %
Adhesion, initial	FINAT FTM-1, stainless steel	540 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	720 N/m
	Glass	640 N/m
	PMMA	640 N/m
	Polycarbonate	640 N/m
Flammability		Self extinguishing
Shelf life	Stored at 22° C/50-55 % RH	2 years
Accelerated ageing	DIN 53387 1500 hours exposure	No negative impact on film performance
Durability **	Vertical exposure	up to 5 years outdoor

Thermal

Application temperature	Minimum: + 10°C
Temperature range	- 50°C to + 100°C

Chemical

Humidity resistance	200 hours exposure	No effect
Chemical solvent resistance		
Test Fluid	Immersion Time	Effect
Distilled Water	24 hours	No effect
Water	24 hours	No effect
Detergent (1% solution)	24 hour	No effect
Detergent solution 65°C	8 hours	No effect
Hydrochloric	10 minutes	No effect
Ammonium Hydroxide	10 minutes	No effect
Isopropyl alcohol/water (20/80)	10 minutes	No effect

Test Methods

Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70°C, after which the shrinkage is measured.

Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

Warranty

Avery® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Durability

Durability is based on exposure conditions in the Asia Pacific region. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing north in the southern hemisphere or south in the northern hemisphere; in areas of long high temperature exposure such as northern Australia; in industrially polluted areas or high altitudes, exterior performance will be decreased.

***Information unavailable at time of printing.